

Yparex® 8903 E

Property Data

Datasheet

PE-VLD modified

19-mrt-19

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Melt flow index MFI (190°C, 2,16 kg)	3,2	g/10 min	ISO 1133
THERMAL PROPERTIES			
Melting temperature (10°C/min)	124	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 10 N)	55	°C	ISO 306
RHEOLOGICAL CALCULATION PROPERTIES			
Enthalpy of melting	72	kJ/kg	ISO 11357-1/-3
OTHER PROPERTIES			
Density	890	kg/m ³	ISO 1183

Visit us at www.yparex.com

Disclaimer
 All information supplied by or on behalf of Yparex BV in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Yparex BV assumes no liability and makes no warranties of any kind, explicitly or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence form the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.

Yparex® and EcoForte® are trademarks of The Compound Company BV.